

PARAGON BUILDING PRODUCTS

PRODUCT INFORMATION ITEM NO. 45455

P-77 CONSTRUCTION GROUT



P-77CONSTRUCTION GROUT: is a nonshrink metallic structural Portland Cement material designed for high strength grouting.

FEATURES AND BENEFITS:

- Non-corrosive, will not attack reinforcement
- ♦ Non-Shrink, no loss of volume
- Non-metallic, non-staining, grey color
- Meets ASTM C 1107 Packaged Dry, Hydraulic Cement Grout (Non-shrink)
- Meets Corps of Engineers Specification CRD-C 621
- Dry Pack, Plastic, or Flow able Consistency
- Pump able for Easy Placement

USES: Grouting of

- ◆ Concrete-poured in place, pre-cast, tilt-up, and pre-stressed
- ♦ Heavy Machinery
- ♦ Steel Bearing Plates
- ♦ Sole Plates
- ◆ Concrete Columns
- ♦ Anchor Bolts
- Dowel Rods
- ◆ Reinforcing Steel in Block Cells

PREPARATION: Selection of the grout is to be done by the engineer, Remove all unsound concrete, grease, oil, paint, and any other foreign material that will inhibit performance. Prior to grout placement, all surface must be clean and saturated with water for 24 hours. Remove excess water before placing the grout. Provide air beneath structural system.

PREPARATION (cont): Suggestions in

Form Work Wood form work or other absorbent forms should be coated with a form release oil to prevent grout adherence and excessive water absorption. Design form work to facilitate rapid, continuous and complete filling of the space to be grouted.

Use methods that will enable the grout to flow by gravity between the surfaces and keep the grout in full contact with these surfaces until it has hardened.

For dry pack application, refer to: Portland Cement Association <u>— Cementitious</u> <u>Grouts and Grouting (EBI 11.O1T.</u>

The Form work must be rigid and well secured to withstand the impact of grout placement.

MIXING: Add only clean water. The water quantities shown are approximate and may vary slightly with type of equipment and application conditions. For optimum application and product performance:

Mix Temperature	Storage for 12-24
at time of placement	hrs. prior to mixing
Standard 60°F - 70°F	60°F - 70°F
Metric 15 5C° - 21 1°C	$15.5^{\circ}C = 21.2^{\circ}C$

Hot weather Cold weather application: application: (90°F) (32.2°C) (50°F) (10.0°C)

Water Temperature:

Standard 45°F --- 80°F Metric 7.2°C --- 26.6°C

Water demand and mix temperature must be determined using standard test methods for consistency and temperature measurement at the time of application.

Desired Grout Consistency:

Plastic (Trowel Consistency)

Grout Water Yield Unit Wt.
Standard: 55 lbs. 7 pt. .50 Cu. ft. 125 lbs. Cu. ft.

Metric: 24.9 kg 3.98 L 0.014cm³ 56.75 kg/r n³



PARAGON BUILDING PRODUCTS

PRODUCT INFORMATION ITEM NO. 45455

P-77 CONSTRUCTION GROUT

PREPARATION (cont):

Flow-able (Pumping Consistency)

	Grout	Water	Yield	Unit Wt.
Standard:	55 lbs.	1 Gal	.51 Cu. ft.	126 lbs. Cu. ft.

Metric: 24.9 kg 4.546 L 0.017 cm³ 57.2 kg/r n³

Use a mixer large enough to permit continuous placement before any part of the grout has set.

PLACEMENT:

Place the grout quickly. Rodding the grout lightly will help remove air bubbles. Avoid vibration which can cause bleeding and segregation, Shut down nearby machines.

Placement Temperature

Substrate	Minimum 50°F (10.0 C)	Maximum 90°F (32.2 C)
Mix	60°F (15.5 C)	70°F (21.1C)
Air	50°F (10.0 C)	90°F (32.2 C)

CURING: Forms may be removed as soon as the grout is firm and cannot be penetrated by a pointed masonry trowel. Exposed shoulders can be left in place or trimmed. After the forms are removed, prevent evaporation by keeping the exposed surfaces wet for several hours, Protect from freezing for a minimum of 48 hours after placing. P-77 Construction Grout can be exposed under normal weather conditions. For installations where acids and sulfates are present, a protective coating is required.

Cure per Portland Cement Association – <u>Design</u> and Control of Concrete Mixes (EBOO1.12T) and/or American Concrete Institute 308 – <u>Standard Practice for Curing Concrete</u>.

TECHNICAL DATA:

	Piastic	Flow-able
Water	13%	15%
Compressiv	e Strength ASTM	C 942

24 hours 3,400 psi (23.4) 2,200 psi (15.1 mpa)

3 days 6,700 psi (46.2) 6,500 psi (44.8 mpa)

7 days 7,800 psi (53.7 7,400 psi (51.0 mpa)

28 days 9,000 psi (62.0) 8.800 psi (60.6 mpa)

TECHNICAL DATA (cont):

Set Time ASTM C 191

Initial 4:40 5:30

Final 6:30 7:30

Consistency Flow ASTM C 230

Volume Change, % Expansion ASTM C 827

At final set +0.38 +0.08

After 24 hours +0.30 +0.04

Paragon P-77 Construction Grout meets the performance requirements of ASTM CRD-C 621 for grades A, B and C specifications for non-shrink grout over a wide temperature range.

3 days	+0.07	+0.07
7 days	+0.07	+0.07
14 days	+0.07	+0.05
28 days	+0.07	+0.05

PACKAGING:

55 Lb. / 24.9 kg. Multiply bag

COVERAGE (approximate):

1 cu. ft. (0.028 m3): 2 bags/110 lbs. (50 kg)

1 cu. yd. (0.76 m3): 54 bags/2970 lbs. (1348 kg)

100 sq. ft. (2.8³) @ 1" (2.5 cm): 17 bags/935 lb. (424 kg)

COLOR: Grey



PARAGON BUILDING PRODUCTS

PRODUCT INFORMATION ITEM NO. 45455

P-77 CONSTRUCTION GROUT

LIMITATIONS:

- ♦ **DO NOT** apply when the air or substrate temperature is below 40° F within 24 hours of application.
- ♦ **DO NOT** over water
- ◆ DO NOT apply over substrates that are frozen or contain frost
- ◆ DO NOT use vibrators in placing the grout
- ♦ **DO NOT** use dirty water or tool
- DO NOT add or mix any materials with this product unless approved by PARAGON CONCRETE PRODUCTS INC.
- ♦ **DO NOT** accelerate cure with fans

CAUTION: Contains Portland Cement. Cement causes skin irritations, may cause allergic reactions. Avoid eye contact or prolonged contact with skin. Use of a dust respirator, safety goggles and rubber gloves are recommended. Wash self thoroughly after any contact. In case of eye contact, flush immediately with plenty of water for at least 15 minutes. Consult a physician immediately.

KEEP OUT OF REACH OF CHILDREN

Avoid hazards by following all precautions found in the MSDS (Material Safetl Data Sheet), product labels and product information sheets. Please read this information prior to using the product.

TECHNICAL SERVICE:

For, application procedures or surface conditions not specified in literature contact:

Paragon Concrete Products Inc. 2305 S Roof Tile Rd Casa Grande, AZ 85193 Phone: 520-836-6454 Fax: 520-421-1172

Avoid hazards by following all precautions found in the SDS (Safety Data Sheet), product labels and product information sheets. Please read this information prior to using the product. SDS are available through technical service at 520-836-6454.

LIMITED WARRANTY:

Paragon Building Products, Inc. (Paragon) warrants that this product and the materials used therin meet or exceed the applicable **ASTM** standards listed and in force at the time of manufacture. Paragon will replace any product or part which proves defective due to quality of ingredients used od due to the manufacturing process itself. This warranty shall apply only if the product is used in stict accordance to applicable specifications and instructions provided by Paragon for its use, and Paragon shall not be liable otherwise, Replacement of any defective product or, at Paragon's option, refund of the purchase price of any defective product shall be the buyers sole remedy under this warranty, and Paragon shall in no event be liable for any damages in excess of the purchase price of the defective product. PARAGON SHALL IN NO EVENT BE LIABLE FOR ANY CONSEQUENTIAL INCIDENTAL OR SPECIAL DAMMAGES.

This Warranty constitutes the sole warranty given by Paragon in connection with this product, and Paragon has authorized no person to make or give any other warranties or representations, oral or written on its behalf. IN PARTICULAR, THER ARE NO IMPLIED WARRANTIES, INCLUDING WITHOUT EXCEPTION WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No modifications of this warranty in favor of any buyer shall be vaid unless given in writing and signed by an officer of Paragon.